

# **Electronic Potting Silicone (Platinum Cured)**


### **Product Description:**

Platinum cure electronic potting silicone rubber is two parts with low viscosity, and it can be cured completely at room temperature. Platinum cure electronic potting silicone rubber is with stronger heat-resistance than that of condensation type.

# **Application:**

it is mainly applied for the surface of polycarbonate, PP, ABS, PVC, metal etc., which is suitable for the electronic moisture-proof and waterproof, fixed. It is applicable to sealing bonding coating LED for electronic parts.





#### Appearance:

Part A: an non-toxic and odorless liquid in transparent color with platinum inside Part B: an non-toxic and odorless liquid in transparent color.

ATT: We do any curing time as you requirements

#### **Characteristics**

Electronic potting silicone rubber is a kind of two component (1:1 mixing ratio) platinum cure silicone with characteristics of heat-conducting, low viscosity, inherent flame resistance, waterproofing, etc.

It can cure both at room temperature and heated temperature and the curing time can be accelerated by higher temperature.

Web:www.ottsilicone.comPage 1Email:sz@ottsilicone.comTel:+86-020-86819712Email:gz@ottsilicone.com



# **Guangzhou OTT New Materials Co., Ltd.**

## Features:

- ♦ Great fluidity
- ♦ Platinum based, environmental,odorless and nontoxic
- ♦ Mixing ration: 1:1 and 10:1 are available
- ♦ Perfect adhesion
- ♦ electrically insulative
- ♦ optically clear
- ♦ Resistant to radiation&abrasion
- ♦ heat-conducting.
- ♦ Inherent flame resistance
- ♦ High resistance to high temperature and aging(resist -60 to 250°C)

Model Code: D8105#, D8110#, D8115#, D8120#, D8125#

## Technical Data:

**Notes:** The data are based on the operation under room temperature of 25  $^{\circ}$ C.

Typical general characteristics	Inspection Method	Model Code				
Product data (Catalyzed A+B)	/	D8105	D8110	D8115	D8120	D8125
Hardness	Shore A	5±2	10±2	15±2	20±2	25±2
Mix Ratio	A:B	10:1/1:1				
Color	1	Transparent				
Pot life	25 °C (77F)	1- 60mins				
Curing Time	25 °C (77F)	0.5- 24h				
Viscosity	cps	1000±500				
Dielectric permittivity	1.2MHz	3.0~3.3				
volume resistivity	(Ω·cm)	≥1.0×1014				
Fire resistance	/	UL94V1				
Dielectric Strength	(kV/mm)	≥25				
Thermal Conductivity	(W (m·K)	≥0.3				

Web:www.ottsilicone.comPage 2Email:sz@ottsilicone.comTel:+86-020-86819712Email:gz@ottsilicone.com



**Guangzhou OTT New Materials Co., Ltd.** 

# Packing:

**Part A:** 1kg, 5kg, 10kg, 20kg, 25kg, 200kg, Vacuumed Packing in white color **Part B:** 1kg, 5kg, 10kg, 20kg, 25kg, 200kg, Vacuumed Packing in sky blue color



# Storage & Shelf Life:

1Year at least, stored in a cool and dry place under room temperature 25°C

# **Operation Method:**

- 1. Pouring by man making
- 2. Injecting by machine



# Caution - Safety First !!!

- 1. Read the material safety data sheet(MSDS) before use.
- 2. Keep Out Of Reach Of Children.
- 3. Be careful. Use only with adequate ventilation. Contact with skin and eyes may cause irritation. Flush eyes with water for 15mins and seek immediate medical attention. Remove from skin with water-less hand cleaner followed by soap & water.



Web:www.ottsilicone.comPage 3Email:sz@ottsilicone.comTel:+86-020-86819712Email:gz@ottsilicone.com